



## General Description

Junckers prefinished lacquered floors have a hard-wearing factory applied polyurethane lacquer surface, and require no treatment prior to use.

The life span of the lacquered surface largely depends on proper cleaning and maintenance.

However, in high-traffic areas, areas subject to spillages of liquids and floors subject to a high degree of maintenance, consideration should be given to a further coat of Junckers lacquer.

## Cleaning and Maintenance

### Daily/Weekly

Vacuum and/or sweep the floor to remove surface dust and grit. Occasionally, clean the floor with a mild solution of **Junckers SYLVA CLEANER**. Use a well wrung out cloth, a hand held sprayer or mop kit in combination with a rotary polishing machine mounted with a soft pad or a Rotowash machine.

Floors that have been newly lacquered should not be cleaned for 3 days after lacquering.

### Important!

Always use as little water as possible for cleaning. Use well wrung out cloths or mops and remove excess water immediately. Wipe up any spillage of water as soon as possible to prevent the wood becoming damaged.

### Periodic Maintenance

Clean the floor using **Junckers SYLVA Cleaner**. Apply a thin coat of diluted **Junckers SYLVApolish** on the clean surface. Use approx. 0.1 liters **Junckers SYLVApolish** to 10 liters of water and a well wrung out cloth. In high-traffic areas apply undiluted **Junckers SYLVApolish** for extra protection.

Intervals between treatments depend on the degree of traffic.

### Long Term Maintenance

Remove old grease, dirt, and polish with **Junckers SYLVAstrip**. Add approx. 0.2 litres **Junckers SYLVAstrip** to 10 litres 25°C warm water. Use a well wrung out cloth. Repeat the procedure if necessary. Before treatment with **Junckers SYLVApolish**, wipe the floor using clean water and a well wrung out cloth.

### Important!

Floors maintained with **Junckers SYLVApolish** should not be buffed.

## Relacquering

To preserve a hardwearing surface, clean the floor with **Junckers SYLVAstrip**, sand it and relacquer the dust-free surface. Sanding and cleaning are crucial to achieving optimum adherence.

Products for finishing of floors are supplied from Junckers on request.

### Important!

Floors previously treated with wax or polish must be machine-sanded before lacquering with Junckers seals.

## Further technical information

Cleaning and Maintenance: G 1.0 - General information for floors

Products:

F 4.7 - Junckers SYLVApolish  
F 4.8 - Junckers SYLVAstrip  
F 10.2 - Junckers SYLVA Cleaner